

# SPECIFICATION DATA

## 1. Product Name

Foam it Green® 202 and 602 Class I Slow Rise Disposable Foam Kits

## 2. Manufacturer

A&B Filling, Inc.  
 PO Box 510803 | New Berlin, WI 53151  
 Phone: 1-833-362-6484  
 Fax: 1-833-362-6484  
 Email: sales@foamitgreen.com  
 Web: www.foamitgreen.com



## 3. Product Description

Foam it Green® 202 and 602 Class I Slow Rise are disposable, closed-cell, low-pressure spray foam kits consisting of two chemical components (Component A: isocyanate and Component B: polyol blend), patented U-Control dispensing gun, ten multi-purpose mixing nozzles, nitrile gloves, and packet of petroleum jelly. These systems contain a flame retardant formula, meeting requirements of ASTM E-84 as a Class I product. They do not require any external power source.

## 4. Technical Data

Foam it Green® 202 and 602 Class I Slow Rise have the following physical properties:

### DENSITY (ASTM D1622):

Free Rise	1.75 lb/f <sup>3</sup>
In Place	2.0 lb/f <sup>3</sup>

**R FACTOR** at 1" thickness (ASTM C518): 6.7

**COMPRESSIVE STRENGTH** (ASTM D1621): 15.9 psi (parallel)

**CLOSED CELL CONTENT** (ASTM D2856): >95%

### DIMENSIONAL STABILITY (ASTM D2842):

% Volume Change, 158°F, 100 RH, 7 days	3.13
% Volume Change, -80°F, 7 days	-0.29

### DIMENSIONAL STABILITY (ASTM D2126):

% Volume Change, 158°F, 100 RH, 7 days	2.01
% Volume Change, -60°F, 7 days	-0.42

### TEMPERATURE TOLERANCE:

High Temperature Tolerance	250° F
Low Temperature Tolerance	-250° F

**AIR BARRIER PROPERTIES** at 75 Pa (ASTM E283): 0.005 L/s/m<sup>2</sup>

**PERM RATING** at 1" / at 3" (ASTM E96): 3.70 Perms / 1.83 Perms

**TENSILE STRENGTH** (ASTM D1623): 36.14 psi

**FLAMESPREAD** at 2" thickness (ASTM E84): 20

**SMOKE DEVELOPED** at 2" thickness (ASTM E84): 300

**FUNGI RESISTANCE** (ASTM G21) No Growth

**TACK FREE TIME:** 2 minutes

**RISE TIME:** 2 minutes

### YIELD:

202 Class I Slow Rise	16.5 f <sup>3</sup>   200 f <sup>2</sup> @ 1" thick
602 Class I Slow Rise	50 f <sup>3</sup>   600 f <sup>2</sup> @ 1" thick

- Foam it Green® products do not contain any CFC's, Penta-BDE's, VOC's, or Urea-Formaldehyde.
- Published yields are theoretical and vary based on several factors, including ambient conditions and specific application.
- Always use recommended personal protective equipment when using polyurethane foam products. Refer to the Material Safety Data Sheet for additional information on safe use and handling of Foam it Green® Systems.

