

# SPECIFICATION DATA



## 1. Product Name

Foam it Green® Foam it 12, 102, 202 and 602 Class I Disposable Foam Kits

## 2. Manufacturer

A&B Filling, Inc.  
 PO Box 510803 | New Berlin, WI 53151  
 Phone: 1-833-362-6484 Fax: 1-833-362-6484  
 Email: sales@foamitgreen.com  
 Web: www.foamitgreen.com

## 3. Product Description

Foam it Green® Foam it 12 Class I, 102 Class I, 202 Class I, and 602 Class I are disposable, closed-cell, low-pressure spray foam kits consisting of two chemical components (Component A: isocyanate and Component B: polyol blend), patented U-Control dispensing gun, two multi-purpose mixing nozzles (System 12) or ten multi-purpose mixing nozzles (Systems 102, 202 and 602), nitrile gloves, and packet of petroleum jelly. These systems contain a flame retardant formula, meeting requirements of ASTM E-84 as a Class I product. They do not require any external power source.

## 4. Technical Data

Foam it Green® Foam it 12, 102, 202 and 602 Class I have the following physical properties:

### DENSITY (ASTM D1622):

Free Rise	1.75 lb/f <sup>3</sup>
In Place	2.0 lb/f <sup>3</sup>

**R FACTOR** at 1" thickness (ASTM C518): 6.7

**COMPRESSIVE STRENGTH** (ASTM D1621): 15.9 psi (parallel)

**WATER ABSORPTION** (ASTM D2842):  
 % Volume Change / Lbs/Ft<sup>2</sup> 2.96% / 0.46

**CLOSED CELL CONTENT** (ASTM D2856): >95%

**DIMENSIONAL STABILITY** (ASTM D2842):  
 % Volume Change, 158°F, 100 RH, 7 days 3.13  
 % Volume Change, -80°F, 7 days -0.29

**DIMENSIONAL STABILITY** (ASTM D2126):  
 % Volume Change, 158°F, 100 RH, 7 days 2.01  
 % Volume Change, -60°F, 7 days -0.42

**TEMPERATURE TOLERANCE:**  
 High Temperature Tolerance 250° F  
 Low Temperature Tolerance -250° F

**AIR BARRIER PROPERTIES** at 75 Pa (ASTM E283): 0.005 L/s/m<sup>2</sup>

**PERM RATING** at 1" / at 3" (ASTM E96): 3.70 Perms / 1.83 Perms

**TENSILE STRENGTH** (ASTM D1623): 36.14 psi

**FLAMESPREAD** at 2" thickness (ASTM E84): 20

**SMOKE DEVELOPED** at 2" thickness (ASTM E84): 300

**FUNGI RESITANCE** (ASTM G21) No Growth

**TACK FREE TIME:** 30-40 seconds

**RISE TIME:** 30-40 seconds

**YIELD:**

System 12 Class I	1 f <sup>3</sup>   12 f <sup>2</sup> @ 1" thick
System 102 Class I	9 f <sup>3</sup>   108 f <sup>2</sup> @ 1" thick
System 202 Class I	16.5 f <sup>3</sup>   200 f <sup>2</sup> @ 1" thick
System 602 Class I	50 f <sup>3</sup>   600 f <sup>2</sup> @ 1" thick

- Foam it Green® products do not contain any CFC's, Penta-BDE's, VOC's, or Urea-Formaldehyde.
- Published yields are theoretical and vary based on several factors, including ambient conditions and specific application.
- Always use recommended personal protective equipment when using polyurethane foam products. Refer to the Material Safety Data Sheet for additional information on safe use and handling of Foam it Green® Systems.



## **5. Code Compliances**

Foam it Green® Class I systems comply with the following codes:

- National Fire Protection Association – per NFPA 286 testing, cured product can be left exposed in a non-fire-resistant-rated roof/wall juncture, when applied at a maximum 6" high and 2" deep (unlimited width).